

## TUBOSIL - FVMQ/NMX



### MATERIAL

VMQ (Vinyl Methyl Quality) silicone hoses with aramidic textile reinforcements and Fluorosilicone underlay (FVMQ)

### APPLICATION








Connection between radiators and internal combustion engines, between turbine and intercooler on cars, trucks, industrial vehicles and generators, for the passage of antifreeze liquids mixed with water, oils and benzenes

### TEMPERATURE RANGE

-55 °C up to +225 °C with peaks to +250°C

### COLOUR

Red iron oxide with black interior

 Inner diameter (mm)	 Wall thickness (mm)	 Reinforcement number	 Wall thickness tolerance (mm)	 Burst pressure (bar)	 Hardness (Shore A)	 Length (mm)
6,5	4,0	3	+1 / -0,5	45	65 - 75	1000 - 4000
8	4,0	3	+1 / -0,5	45	65 - 75	1000 - 4000
9,5	4,0	3	+1 / -0,5	35	65 - 75	1000 - 4000
11	4,0	3	+1 / -0,5	35	65 - 75	1000 - 4000
13	4,0	3	+1 / -0,5	35	65 - 75	1000 - 4000
16	4,0	3	+1 / -0,5	30	65 - 75	1000 - 4000
19	4,0	3	+1 / -0,5	28	65 - 75	1000 - 4000
22	4,0	3	+1 / -0,5	19,3	65 - 75	1000 - 4000
25	4,0	3	+1 / -0,5	19,3	65 - 75	1000 - 4000
28	4,5	3	+1 / -0,5	19,3	65 - 75	1000 - 4000
30	4,5	3	+1 / -0,5	15,4	65 - 75	1000 - 4000
32	4,5	3	+1 / -0,5	15,4	65 - 75	1000 - 4000







Tubi Flessibili S.r.l. - Tel: +39 0131238971 - Email: [info@tubiflessibili.net](mailto:info@tubiflessibili.net)

According to ISO 1307

Above technical data are referring to applications at a room temperature (+20°C)

Copyright © TUBI FLESSIBILI S.r.l. - All rights reserved. The texts and images are property of Tubi Flessibili S.r.l. Even partial reproduction of the catalog is prohibited.



 Inner diameter (mm)	 Wall thickness (mm)	 Reinforcement number	 Wall thickness tolerance (mm)	 Burst pressure (bar)	 Hardness (Shore A)	 Length (mm)
35	4,5	3	+1 / -0,5	15,4	65 - 75	1000 - 4000
38	4,5	3	+1 / -0,5	15,4	65 - 75	1000 - 4000
40	4,5	3	+1 / -0,5	15,4	65 - 75	1000 - 4000
45	4,5	3	+1 / -0,5	14	65 - 75	1000 - 4000
48	4,5	3	+1 / -0,5	14	65 - 75	1000 - 4000
51	5,0	4	+1 / -0,5	14	65 - 75	1000 - 4000
53	5,0	4	+1 / -0,5	14	65 - 75	1000 - 4000
55	5,0	4	+1 / -0,5	13	65 - 75	1000 - 4000
57	5,0	4	+1 / -0,5	12	65 - 75	1000 - 4000
60	5,0	4	+1 / -0,5	10	65 - 75	1000 - 4000
63	5,0	4	+1 / -0,5	10	65 - 75	1000 - 4000
65	5,0	4	+1 / -0,5	10	65 - 75	1000 - 4000
68	5,0	4	+1 / -0,5	8	65 - 75	1000 - 4000
70	5,0	4	+1 / -0,5	8	65 - 75	1000 - 4000
76	5,5	4	+1 / -0,5	8	65 - 75	1000 - 4000
80	5,5	5	+1 / -0,5	8	65 - 75	1000 - 4000
83	5,5	5	+1 / -0,5	5,5	65 - 75	1000 - 4000
90	5,5	5	+1 / -0,5	5,5	65 - 75	1000 - 4000
102	5,5	5	+1 / -0,5	5	65 - 75	1000 - 4000
114	5,5	5	+1 / -0,5	5	65 - 75	1000 - 4000
127	5,5	5	+1 / -0,5	5	65 - 75	1000 - 4000
152	5,5	5	+1 / -0,5	5	65 - 75	1000 - 4000

